



TECHNICAL INFORMATION	English	Metrics	Test Method
Absorption by Weight, %	0.15	0.15	(C97)
Density, Lbs/Ft ³ (Kg/m ³)	179	2.867.3	(C97)
Compression Strength, psi (MPa)	26.124	180.29	(C170)
Abrasion Resistance, Hardness	110	N/A	(C241)
Flexural Strength, psi (mpa)	4178	33.37	(C880)